



2200. E. House St
 Alvin, TX 77511
 Phone: 281-585-6700
 Fax: 281-585-6701



SPS. Galv. Structural Bridge Rope to ASTM A-603

Nominal Diameter Inches	Weight per Ft. Approx, Lb	Metallic Area. Sq. Approx. Inch	Breaking Strength		
			(Tons)		
			Class A	Class B	Class C
3/8	0.24	0.065	6.5	6.2	5.9
7/16	0.32	0.091	8.8	8.4	8.0
1/2	0.42	0.119	11.5	11.0	10.5
9/16	0.53	0.147	14.5	13.8	13.2
5/8	0.65	0.182	18.0	17.2	16.4
11/16	0.79	0.221	21.5	20.5	19.5
3/4	0.95	0.268	26.0	24.8	23.6
13/16	1.10	0.311	30.0	28.6	27.3
7/8	1.28	0.361	35.0	33.4	31.8
15/16	1.47	0.414	40.0	38.2	36.4
1	1.67	0.471	45.7	43.6	41.5
1,1/8	2.11	0.596	57.8	55.1	52.5
1,1/4	2.64	0.745	72.2	68.9	65.6
1,3/8	3.21	0.906	87.8	83.8	79.8
1,1/2	3.82	1.076	104.0	99.2	94.5
1,5/8	4.51	1.270	123.0	117.0	112.0
1,3/4	5.24	1.470	143.0	136.0	130.0
1,7/8	6.03	1.690	164.0	156.0	149.0
2	6.85	1.920	186.0	177.0	169.0
2,1/8	7.73	2.170	210.0	200.0	191.0
2,1/4	8.66	2.420	235.0	224.0	214.0
2,3/8	9.61	2.69	261.0	249.0	237.0
2,1/2	10.60	2.97	288.0	275.0	262.0
2,5/8	11.62	3.27	317.0	302.0	288.0
2,3/4	12.74	3.58	347.0	331.0	315.0
2,7/8	13.90	3.91	379.0	362.0	344.0
3	15.11	4.25	412.0	393.0	374.0
3,1/4	18.00	5.04	475.0	453.0	432.0
3,1/2	21.00	5.83	555.0	529.0	504.0
3,3/4	24.00	6.67	640.0	611.0	582.0
4	27.00	7.59	730.0	696.0	664.0